

**PRIMER PU-1000 - SINGLE-COMPONENT
POLYURETHANE RESIN AS A PRIMER**

Single component, solvent-content polyurethane resin. It has been specifically designed to increase bonding and improve the surface leveling of the substrates prior to the waterproofing and flooring systems.

USES

For application in the following situations:

- Increase adherence and improve the planimetry of the surfaces such mortar, concretes
- As an adhesion promoter on waterproofing old membranes overlappings

NOTE: call our technical department about the application to other substrates or scopes of use

Density	±1,12 g/cm ³
Viscosity	70~300 cps
Dry time	2~3 hours
Application method	By brush, by a short nap acrylic wool roller, always thin coats application



GENERAL SPECIFICATIONS

- Single-component, solvent-based, polyurethane resin once dry forms a continuous and highly adherent film on supports such as concrete, mortar or wood, increasing adhesion for liquid waterproofing systems.
- Its consumption depends on the situation of the support, irregularities that it presents or level of planimetry. It ranges between 100-200 g/sqm/layer. Apply thin coat, never thick.
- In repairs and membrane overlaps its consumption is between 50-100 g/sqm
- The application must be carried out in conditions of non-presence of moisture in the substrate or water from the substrate or backsplash, either at the time of application or afterward (pressure by groundwater level).
- Possibility of applying in combination with mineral fillers (silica aggregate) on very irregular supports.

PACKAGING

Metallic pail: 5 kg and 20 kg.

SHELF LIFE

12 months at temperatures between 5° C and 35° C (41 °F to 95 °F), provided it is stored in a dry place. Once the tin has been opened, the product must be used.

The following factors prior to application should be checked:



- Previous preparation of the concrete through mechanical processes (milling, sanding, shotblasting or scarifying) to achieve the proper bonding profile (*CSP 3-4-5 according ICRI*) and open the pore
- Existing coves/holes or areas with a lack of material must be repaired using a mixture of our Primer EP-1020 and Silica Sand or Primer EP-1010 epoxy resins.
- Perimetral caulking with Mastic PU
- In joints: remove old material and dirty, clean and fill with Mastic PU. Use also Tecnoband 100 if necessary
- General cleaning of the substrate, removing existing dust, dirt, grease, or efflorescence

?Cement or concrete substrates

- Substrate must be fully cured (the concrete curing process is 28 days). Check the maximum degree of moisture permittivity of the substrate
- Mix the two components using a mechanical shaker for approximately 4-5 minutes (medium speed)
- Apply two or more coats until the desired thickness is obtained (always wait until completely dry time before applying next coat)
- The yield may vary depending on the coats that need to be made according to the type and physical condition of the substrate. Consumption is approximately 150 g/m²/layer; the total consumption can vary from 150 to 200 g/m². Apply always thin coats, never self-levelling or coat too thick. Always respect the recoat time between coats or between different materials. In case of rain, apply a thin layer, consumption approx. 100-150g/sqm.

NOTE: For other types of supports, weather conditions or the substrate to be applied, consult our technical department.

HANDLING AND SAFETY

These safety recommendations for handling, are necessary for the implementation process as well as in the pre and post, on exposure to the loading machinery.

- Respiratory Protection: When handling or spraying use an air-purifying respirator.
- Skin protection: Use rubber gloves, remove immediately after contamination. Wear clean body-covering. Wash thoroughly with soap and water after work and before eating, drinking, or smoking.
- Eye / Face: Wear safety goggles to prevent splashing and exposure to particles in the air.
- Waste: Waste generation should be avoided or minimized. Incinerate under controlled conditions in accordance with local laws and national regulations.

Anyway, consult the material and safety data sheet of the product(MSDS) or contact our technical department.



Unit A6 Rose Industrial Estate, Marlow Bottom, SL7 3ND

T: 01628 476040

www.srsroofsystems.com info@srsroofsystems.com



Finlàndia, 33 · 08520 Les Franqueses del Vallès · Barcelona (Spain)
(+34) 93 568 21 11 · info@tecnopol.es · www.tecnopol.es

TECHNICAL FEATURES

PROPERTIES		RESULT
Density	ISO 1675	1,12 ±0,08 g/cm ³
Viscosity	ISO 2555	70~300 cps
Solids content	ISO 1768	70~75%
VOC compounds A/B	(volatile organic compounds)	250 g/l / 290 g/l
Adhesion to concrete		> 1,5 MPa
Times: dry/ recoat		2~3 hours / 3~48 hours
Application temperature range (substrate / environment)		5°C~35 °C / 5 °C ~ 30 °C (41°F to 95°F / 41°F to 86°F)
Maximum substrate moisture		±4%
Maximum environmental humidity		±80%
Dilution		Desmosolvent

Results performed in the laboratory at 23°C (73°F) and 50% RH, under controllable conditions. These values may vary depending on the application, climatology, or substrate conditions.

The information herein is to assist customers in determining whether our products are suitable for their applications. Our products are only intended for sale to industrial and commercial customers. The customer assumes full responsibility for quality control, testing, and determination of the suitability of products for its intended application or use.

We warrant that our products will meet our written liquid component specifications. We make no other warranty of any kind, either express or implied, by fact or law, including any warranty of merchantability or fitness for a particular purpose since Tecnopól Sistemas S.L.U. does not control the execution, since Tecnopól Sistemas S.L.U. does not control the execution. Our total liability and customers' exclusive remedy for all proven claims is the replacement of the nonconforming product and in no event shall we be liable for any other damages. While descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/ use, Tecnopól Sistemas S.L.U. recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use.

No warranties of any kind, either expressed or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding products described or designs, data or information set forth, or that the products, designs, data or information may be used without infringing the intellectual property rights of others. In no case shall the descriptions, information, data or designs provided be considered a part of Tecnopól Sistemas S.L.U. terms and conditions of sale. Further, the descriptions, designs, data, and information furnished by Tecnopól Sistemas S.L.U. hereunder are given gratis and Tecnopól Sistemas S.L.U. assumes no obligation or liability for the description, designs, data or information is given or results obtained, all such being given and accepted at the reader's risk.

All data furnished refers to standard production using manufacturing testing tolerances. The product user, and not Tecnopól Sistemas S.L.U., is responsible for determining the suitability and compatibility of our products for the final user's intended use.

The liability of Tecnopól Sistemas S.L.U. and its affiliates for all claims is limited to the purchase price of the material.

Products may be toxic and require special precautions in handling. Users should obtain detailed information on toxicity, together with proper shipping, handling and storage procedures, and comply with all applicable safety and environmental standards.

No freedom from any patents or other industrial or intellectual property rights is granted or to be inferred.

